



Water Resistant Silica Gel

Description:

JZ-WASG & JZ-WBSG has good water-tolerant property, low break-down rate of reclamation and long service life, etc.

Applications:

Mainly used for drying in the air separating process, the adsorption of acetylene in preparation of liquidified air and liquidified oxygen. It is also used for drying compressed air and various industrial gases. In petrochemical industry, electric power industry, brewing industry and other industries, etc. it is used as liquid adsorbent and catalyst carrier. It may also be used as buffer drier, silica sand etc. for ordinary silica protective bed.

Specification:

Standard Package:

Data	Unit	JZ-AWSG	JZ-BWSG
Size	mm	2-5mm ; 4-8mm	
Crush Strength	≥N/Pcs	30	30
Bulk Density	g/L	600-700	400-500
Qualified size ratio	≥%	85	85
Wear rate	≤%	5	5
Pore volume	≥mL/g	0.35	0.70
Qualified ratio of spherical granuales	≥%	90	90
Loss on heating	≤%	5	5
Non-breaking ratio in water	≥%	90	90

Standard Package:

25kg/kraft bag

Attention:

The product as desiccant cannot be exposed in the open air and should be stored in dry condition with air-proof package.

CÔNG TY TNHH TM & DV CH VIỆT NAM

VP Giao Dịch : Số 73C/291/42 - Lạc Long Quân - Nghĩa Đô - Cầu Giấy - HN
Trạm bảo hành 24/7: Số 12 ngõ 190/5 - Thanh Am - Long Biên Hà Nội
CN Miền Nam: 150/10 - HT13, KP2, Hiệp Thành , Quận 12, Tp. Hồ Chí Minh
Điện thoại: 024.6.6868.111 Hotline: 0909.514.123

