

GM - TECH

German tech nitro generator



Silica Gel JZ-ASG

Description:

JZ-ASG silica gel is transparent or translucent.

Average pore diameter: 2.0-3.0nm

Specific surface area: 650-800 m²/g

Pore volume: 0.35-0.45 ml/g

Thermal conductivity : 0.63KJ/m.Hr.°C

Specific heating: 0.92 KJ/m.Hr.°C

Applications:

1-Mainly used for drying and moisture proof.

2-Also be used as catalyst carriers, adsorbents

3-As separators and variable-pressure adsorbents etc.

Specification:

Data	unit	spehre	
Particle Size	Mm	2-4;3-5	
Adsorption Capacity(25°C)	RH=20%	≥%	10
	RH=50%	≥%	22
	RH=90%	≥%	32
Loss on Heating	≤%	5	
Qualified size ratio	≥%	90	
Qualified Ratio of spherical granuales	≥%	90	
Bulk Density	≥g/L	670	

Standard Package:

25kg/woven bag

Attention:

The product as desiccant cannot be exposed in the open air and should be stored in dry condition with air-proof package.

CÔNG TY TNHH TM & DV CH VIỆT NAM

VP Giao Dịch : Số 73C/291/42 - Lạc Long Quân - Nghĩa Đô - Cầu Giấy - HN

Trạm bảo hành 24/7: Số 12 ngõ 190/5 - Thanh Am - Long Biên Hà Nội

CN Miền Nam: 150/10 - HT13, KP2, Hiệp Thành , Quận 12, Tp. Hồ Chí Minh

Điện thoại: 024.6.6868.111

Hotline: 0909.514.123

