



## Activated Alumina JZ-K1

### Description:

It is made of aluminium oxide(alumina; $Al_2O_3$ )

### Applications:

1. drying in electronic, textile and oxidizing industry,
2. adsorbent in air-grading industry(dew-point below -55). it's especially suitable for atmospheric temperature recovering equipment

### Specification:

Properties	Unit	JZ-K1							
Diameter	mm	0.4-1.2	1.0-1.6	2-3	3-4	3-5	4-6	5-7	6-8
Bulk Density	$\geq g/ml$	0.75	0.75	0.7	0.7	0.68	0.68	0.66	0.66
Surface Area	$\geq m^2/g$	300	300	300	300	300	280	280	280
Pore Volume	$\geq ml/g$	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Crush Strength	$\geq N/Pc$	/	25	70	100	150	160	170	180
L.O.I.	$\leq \%$	8	8	8	8	8	8	8	8
Attrition Rate	$\leq \%$	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3

### Standard Package:

25 kg/woven bag  
150 kg/steel drum

### Attention:

The product as desiccant cannot be exposed in the open air and should be stored in dry condition with air-proof package.

## CÔNG TY TNHH TM & DV CH VIỆT NAM

VP Giao Dịch : Số 73C/291/42 - Lạc Long Quân - Nghĩa Đô - Cầu Giấy - HN  
Trạm bảo hành 24/7: Số 12 ngõ 190/5 - Thanh Am - Long Biên Hà Nội  
CN Miền Nam: 150/10 - HT13, KP2, Hiệp Thành , Quận 12, Tp. Hồ Chí Minh  
Điện thoại: 024.6.6868.111      Hotline: 0909.514.123

